

HARZ Labs Dental Model Light Grey

Material Technical Data Sheet (TDS)

Version 1.2 / EN 16 December 2022



SECTION 1: DESCRIPTION AND APPLICATION

Dental Model Light Grey is matte light grey colored resin. Designed for dental demonstration models and master-models. Tough, hard, stable to high temperatures during thermoforming aligners and has low shrinkage.

SECTION 2: MATERIAL PROPERTIES

2.1 Characteristics of liquid

Tested property	Standard/Method	Result (Metric)
Color	-	Light grey (opaque)
Odor	-	Weak
Density	ASTM D1298	1.05-1.20 g/cm ³
Viscosity (25 °C)	ASTM D2393	600 - 1200 mPa·s

2.2 Mechanical properties

Tested property	Standard/Method	Result (Metric)
Flexural Strength	ASTM D790	100 ± 10 MPa
Flexural Modulus	ASTM D790	2300 ± 200 MPa
Ultimate Tensile Strength	ASTM D638	75 ± 7.0 MPa
Elongation at Break	ASTM D638	8.0 ± 1.0 %
Tensile Modulus	ASTM D638	1200±120 MPa
Hardness	ASTM D2240	86 ± 2, Shore D
HDT @ 0.45 MPa	ASTM D648	82 ± 3 °C
HDT @ 1.82 MPa	ASTM D648	65 ± 1 °C
IZOD Impact (Unnotched)	ASTM D4812	4.8 ± 1.2 kJ/m ²

2.3 Special parameters

Tested property	Standard/Method	Result
Solubility (24h)	ASTM D3132	≤ 0.01 %
Sorption (24h)	ASTM D570	≤ 0.47 %
Free Monomer Extraction	ISO 10993	Passed
Cytotoxicity	ISO 10993	Passed
Irritation	ISO 10993	Passed
Sensitization	ISO 10993	Passed

The information above is believed to be accurate and represents the best information currently available to us. All test specimens were printed, cleaned, and post-processed per instructions provided by HARZ Labs company. Results provided here are representative of these processes and may vary if these established protocols are not followed. Users should make their own investigations to determine the suitability of the information for their particular purposes. In no event shall HARZ Labs LLC (OOO «XAPL Лабс») be liable for any claims, losses, or damages of any third party or for lost profits or any special, indirect, incidental, consequential or exemplary damages, howsoever arising, even if HARZ Labs LLC (OOO «XAPL Лабс») has been advised of the possibility of such damages.